## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

SERIZAWA, Kazuya; TAKAHASHI, Katsuhiko

International Application No. PCT/JP99/05666

Serial No. NOT YET ASSIGNED

International Filing Date: 14 October 1999 (14.10.99)

Filed: May , 2001

is 3mm or less.

For: GAS GENERATOR COMPOSITION

## ATTACHMENT 3

## Please add the following new claims 12-20 as follows:

A3

- 12.. The gas generating composition as recited in claim 1, wherein the ammonium nitrate has an average particle size of 1 to  $1000\,\mu\,\text{m}$ , and the microcrystalline carbon has an average particle size of 1 to  $500\,\mu\,\text{m}$  and has a specific surface of 5 to  $1600\,\text{m}^2/\text{g}$ , and the stabilizer has an average particle size of 0.1 to  $500\,\mu\,\text{m}$ .
- 13. The gas generating composition as recited in claim 1, wherein the ammonium nitrate is phase-stabilized ammonium nitrate.
- 14. The gas generating composition as recited in claim 1, wherein the gas generating composition further comprises a high energy substance.
- 15. The gas generating composition as recited in claim 1, wherein the gas generating composition further comprises a binder and a plasticizer.
- 16. The gas generating composition as recited in claim 1, wherein the gas generating composition is formed into a cylindrical body that has an outer diameter of 5 to 40mm and a length of 5 to 40mm and has 7 or 19 substantially equally spaced bores with an inner diameter of 1 to 10mm extending langitudinally therethrough, and the thickness from a surface of the cylindrical body to the bore

nssssk

- 18. The gas generating composition as recited in claim 1, wherein the gas generating composition is molded into a cylindrical body that has an outer diameter of 0.5 to 5mm and a length of 0.5 to 5mm and has a bore with an inner diameter of 0.1 to 4mm extending longitudinally at the center thereof, and the thickness from a surface of the cylindrical body to the bore is 1mm or less.
- 19. The gas generating composition as recited in claim 1, wherein the stabilizer is at least one selected from the group consisting of diphenylamine, resorcinol, and diethyldiphenyl urea.
- 20. A method for manufacturing a molded product of a gas generating agent, the method comprising the steps of:

adding an organic solvent to a gas generating composition to make it into a block, the generating composition including ammonium nitrate as an oxidizing agent, microcrystalline carbon powder as a reducing agent and a stabilizer, wherein the amounts of the ammonium nitrate, the microcrystalline carbon, and the stabilizer are from 89 to 99wt%, from 1 to 6wt%, and from 0.2 to 6wt%, respectively, with respect to the total amount of the ammonium nitrate, the microcrystalline carbon and the stabilizer; and extruding the block into a desired shape by an extruder.